



GRAFSTAR™

ATJ Grade Graphite

Product Overview

Grade ATJ™ graphite has been an industry standard for years. It is a fine grain, high strength material that can be machined to precise tolerances and a fine surface finish. ATJ™ graphite has unique thermal shock resistance due to the combination of low thermal expansion, high thermal conductivity, and low elastic modulus.

Applications

- Permanent molds
- Composite tooling
- Continuous Casting dies
- Hot pressing molds and punches
- Rocket motor nozzles
- Plungers and Rams

Sizes*

Standard Sizes	
English	Metric
16 x 16 x 72 in	406 x 406 x 1828 mm
12 x 25 x 80 in	305 x 635 x 2032 mm

Typical Properties at Room Temperature**

Characteristic	English Units	WG	Metric Units	WG	SI Units	WG
Bulk Density	lbs/ft ³	110	g/cm ³	1.76	g/cm ³	1.76
Average Particle Size	inches	0.001	mm	0.03	mm	0.03
Specific Resistance	10 ⁻⁴ Ω-in	4.61	μΩm	11.7	μΩm	11.7
Flexural Strength	psi	4500	kg/cm ²	316	MPa	31
Young's Modulus	10 ⁶ psi	1.40	kg/mm ²	984	GPa	9.7
Tensile Strength	psi	3740	kg/cm ²	263	MPa	26
Compressive Strength	psi	9500	kg/cm ²	668	MPa	66
Permeability	Darcy	0.002	Darcy	0.002	Darcy	0.002
Hardness	Rockwell "L"	65	Rockwell "L"	65	Rockwell "L"	65
C.T.E. (to 100 °C)	10 ⁻⁶ / °F	1.7	10 ⁻⁶ / °C	3.1	10 ⁻⁶ / K	3.1
Thermal Conductivity	BTU/hr-ft-°F	70	W/m-K	121	W/m-K	121
Ash Content	%	0.09	%	0.09	%	0.09

Notes:

* Other sizes may be made available upon request.

** Properties listed are typical and cannot be used as accept/reject specifications

