



# GRAFSTAR™ CBY Grade Graphite

## Technical Data Sheet 5080

### Product Overview

GRAFSTAR™ CBY graphite is a general purpose, cost effective extruded graphite with improved strength, structure and density characteristics. It is a low ash graphite for superior oxidation resistance.

### Applications

- Heat treating boats and trays
- Fused refractory molds
- Induction furnace susceptor
- Furnace parts
- Aluminum runout tables

### Sizes

- 10" – 24" x 72" diameter rounds
- 12" x 14" x 72"
- 15" x 30" x 72"
- 17" x 17" x 72"
- 17" x 17" x 88"
- 19" x 19" x 72"
- 24" x 24" x 72" rectangles

### Typical Properties at Room Temperature\*

Characteristic	Unit	WG	AG	Unit	WG	AG
Density	lbs/ft <sup>3</sup>	104		g/cm <sup>3</sup>	1.66	
Maximum Particle Size	inches	0.03		mm	0.76	
Specific Resistance	10 <sup>-4</sup> Ωin	3.2	3.9	μΩm	8.1	9.9
Flexural Strength	psi	2400	1900	kg/cm <sup>2</sup>	170	140
Young's Modulus	10 <sup>6</sup> psi	1.32	0.96	kg/mm <sup>2</sup>	930	680
Tensile Strength	psi	1950	1300	kg/cm <sup>2</sup>	140	90
Compressive Strength	psi	5200	5350	kg/cm <sup>2</sup>	370	380
Permeability	Darcy	0.13	0.16	Darcy	0.13	0.16
Hardness	Rockwell "R"	70		Rockwell "R"	70	
C.T.E. (to 100 °C)	10 <sup>-6</sup> /°F	1.4	2.0	10 <sup>-6</sup> /°K	2.5	3.6
Thermal Conductivity	BTU-ft/hr ft <sup>2</sup> °F	85	75	W/mK	145	130
Ash Content	%	0.07		%	0.07	

#### Notes:

\* Properties listed are typical and cannot be used as accept/reject specifications

© 2020 Amsted Graphite Materials LLC. This information is based on data believed to be reliable but Amsted Graphite Materials LLC makes no warranties, express or implied, as to its accuracy and assumes no liability arising out of its use. The data listed falls within the normal range of product properties but should not be used to establish specification limits or used alone as the basis of design. Amsted Graphite Materials LLC's liability to purchasers is expressly limited to the terms and conditions of sale. GRAFSTAR is a trademark of Amsted Graphite Materials LLC.

